



2033 HERITAGE PARK DR, OKLAHOMA CITY, OK 73120 | 1.800.822.1650

### Polarized Light Microscopy Asbestos Analysis Report

QuanTEM Lab No. 376566	Client: QuanTEM Laboratories, LLC
Account Number: A000	Dee Ammerman
Date Received: 02/21/2025	
Received By: Amanda Bass	
Date Analyzed: 02/25/2025	Project: ACM Survey
Analyzed By: Benjamin Hill	Project Location: 33 Saleen Speedway
Methodology: EPA/600/R-93/116	Project Number: 750 HP

QuanTEM Sample ID	Client Sample ID	Composition	Color / Description	Asbestos (%)	Non-Asbestos Fiber (%)	Non Fibrous
001	1	Layered	Red Floor Tile	Asbestos Present Chrysotile 8	NA	CaCO3 Vinyl
001a		Layered	Black Mastic	Asbestos Present Chrysotile 5	NA	Tar
002	2	Layered	White Texture	Asbestos Present Chrysotile 3	NA	CaCO3 Paint
002a		Layered	White Joint Compound	Asbestos Not Present	NA	CaCO3
002b		Layered	White Drywall	Asbestos Not Present	Cellulose 10 Glass Fiber 5	Gypsum 5
003	3	Homogeneous	Gray Window Glazing	Asbestos Present Chrysotile 4	NA	CaCO3 Binder
004	4	Homogeneous	Blue Boiler Gasket	Asbestos Present Chrysotile 10 Crocidolite 60	Cellulose 20	Binder

Unless otherwise noted, upon receipt the condition of the sample was acceptable for analysis.

QuanTEM is a NVLAP accredited Testing PLM laboratory (Lab Code: 101959-0). This report relates only to the specific items tested. NVLAP accreditation applies only to analysis performed utilizing EPA—40 CFR Appendix E to Subpart E of Part 763 and EPA/600/R-93/116 methods.

This report may not be used to claim product endorsement by NVLAP or any agency of the US Government.

This report may not be reproduced except in full, without the written approval of the laboratory.



2033 HERITAGE PARK DR, OKLAHOMA CITY, OK 73120 | 1.800.822.1650

### Polarized Light Microscopy Asbestos Analysis Report

QuanTEM Lab No. 376566	Client: QuanTEM Laboratories, LLC
Account Number: A000	Dee Ammerman
Date Received: 02/21/2025	
Received By: Amanda Bass	
Date Analyzed: 02/25/2025	Project: ACM Survey
Analyzed By: Benjamin Hill	Project Location: 33 Saleen Speedway
Methodology: EPA/600/R-93/116	Project Number: 750 HP

QuanTEM Sample ID	Client Sample ID	Composition	Color / Description	Asbestos (%)	Non-Asbestos Fiber (%)	Non Fibrous
005	5	Homogeneous	White Popcorn Ceiling	Asbestos Not Present	NA	CaCO3 Gypsum Perlite
006	6	Homogeneous	Yellow Carpet Mastic	Asbestos Not Present	Synthetic	2 Glue
007	7	Homogeneous	White Ceiling Tile	Asbestos Present Chrysotile 3 Amosite 2	Glass Fiber	80 Paint
008	8	Homogeneous	Yellow Insulation	Asbestos Not Present	Glass Fiber	100
009	9	Homogeneous	White Insulation	Asbestos Present Chrysotile 15 Amosite 10	NA	Gypsum
010	10	Homogeneous	Gray Stucco	Asbestos Not Present	NA	CaCO3 Sand Gypsum

Unless otherwise noted, upon receipt the condition of the sample was acceptable for analysis.

QuanTEM is a NVLAP accredited Testing PLM laboratory (Lab Code: 101959-0). This report relates only to the specific items tested. NVLAP accreditation applies only to analysis performed utilizing EPA—40 CFR Appendix E to Subpart E of Part 763 and EPA/600/R-93/116 methods. This report may not be used to claim product endorsement by NVLAP or any agency of the US Government. This report may not be reproduced except in full, without the written approval of the laboratory.



2033 HERITAGE PARK DR, OKLAHOMA CITY, OK 73120 | 1.800.822.1650

**Polarized Light Microscopy Asbestos Analysis Report**

Quantem Lab No. 376566	Client: Quantem Laboratories, LLC
Account Number: A000	Dee Ammerman
Date Received: 02/21/2025	
Received By: Amanda Bass	
Date Analyzed: 02/25/2025	Project: ACM Survey
Analyzed By: Benjamin Hill	Project Location: 33 Saleen Speedway
Methodology: EPA/600/R-93/116	Project Number: 750 HP

Quantem Sample ID	Client Sample ID	Composition	Color / Description	Asbestos (%)	Non-Asbestos Fiber (%)	Non Fibrous
-------------------	------------------	-------------	---------------------	--------------	------------------------	-------------

*Benjamin Hill*  
 Benjamin Hill, Assistant Laboratory Manager

2/25/2025  
 Date of Report

Unless otherwise noted, upon receipt the condition of the sample was acceptable for analysis.

Quantem is a NVLAP accredited Testing PLM laboratory (Lab Code: 101959-0). This report relates only to the specific items tested. NVLAP accreditation applies only to analysis performed utilizing EPA—40 CFR Appendix E to Subpart E of Part 763 and EPA/600/R-93/116 methods.

This report may not be used to claim product endorsement by NVLAP or any agency of the US Government.

This report may not be reproduced except in full, without the written approval of the laboratory.







# ASBESTOS CHAIN OF CUSTODY

2033 Heritage Park Drive, Oklahoma City, OK 73120-7502  
 (800) 822-1650 • (405) 755-7272 • Fax: (405) 755-2058

## LEGAL DOCUMENT - PLEASE PRINT LEGIBLY

<b>Contact Information</b> Company: Quantem Laboratories, LLC Contact: Dee Ammerman Account #: A000 SAMPLED BY: Name: Dee Ammerman		<b>Contact Information</b> Phone: (405) 755-7272 Cell Phone: E-mail: deeammerman@quantem.com Date: 2/20/2025		<b>Project Information</b> Project Name: ACM Survey Project Location: 33 Saleen Speedway Project ID: 750 HP PO. Number: N/A	
<b>RELINQUISHED BY</b> 		<b>DATE &amp; TIME</b> 2/21/2025 4:01 PM		<b>VIA</b> HAND	
<b>RECEIVED BY</b> 		<b>DATE &amp; TIME</b> 2/21/2025 4:01 pm		<b>Report Results (☑ one box)</b> <input type="checkbox"/> Quantem Website <input type="checkbox"/> Email deeammerman@quantem.com <input type="checkbox"/> Other	

For Lab Use Only  
 Lab No. 376566  
 Accept  Reject

### REQUESTED SERVICES (Please ☑ the Appropriate Boxes)

	PLM		TEM		TEM		TURNAROUND TIME	
	Bulk Analysis **	400 Point Count	Air-AHERA	Air-NIOSH 7402	Bulk-Presence / Absence EPA600/R-93/116	Bulk-Quantitative [weight%]- Chatfield	Dust-Presence / Absence	Dust-Quantitative [fibers/sq.cm]- ASTM D5755
<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>

No.	Sample ID (10 Characters Max)	To Be Analyzed	Color	Description	Volume / Area (as applicable)	Comments / Notes
1		<input type="checkbox"/>	Red/ Black	Floor Tile & mastic		
2		<input type="checkbox"/>	White	Textured Drywall		
3		<input type="checkbox"/>	Gray	Window Glazing		
4		<input type="checkbox"/>	Blue	Boiler Gasket		
5		<input type="checkbox"/>	White	Popcorn Ceiling		
6		<input type="checkbox"/>	Yellow	Carpet Mastic		
7		<input type="checkbox"/>	White	Ceiling Tile		
8		<input type="checkbox"/>	Yellow	Insulation		
9		<input type="checkbox"/>	White	Insulation		
10		<input type="checkbox"/>	Gray	Stucco		